

SEAMLESS BOILER TUBE



STANDARD	GRADE	CHEMICAL COMPOSITION					MECHANICAL PROPERTIES		
		C (%)	Si (%)	Mn (%)	P (%)	S (%)	Min Yield Point (Mpa)	Tensile Strength (Mpa)	Minimum Elongation (%)
DIN 17175	ST 35.8	0.17 Max	0.10 - 0.35	0.40 - 0.80	0.030 Max	0.030 Max	235	360 - 480	25

AVAILABLE SIZES AND THICKNESS :

Size	Weight
31.8 mm x	2.9 mm x 7 m 14.5 Kg
	3.2 mm x 7 m 15.8 Kg
38.1 mm x	2.9 mm x 7 m 17.6 Kg
	3.6 mm x 7 m 21.5 Kg
44.5 mm x	2.6 mm x 7 m 18.8 Kg
	2.9 mm x 7 m 20.6 Kg
	3.6 mm x 7 m 25.3 Kg
51.0 mm x	2.9 mm x 7 m 24.0 Kg
	3.2 mm x 7 m 26.4 Kg
	3.6 mm x 7 m 29.5 Kg
63.5 mm x	3.2 mm x 7 m 33.3 Kg
	4.0 mm x 7 m 41.0 Kg

Size	Weight
70.0 mm x	3.2 mm x 7 m 36.9 Kg
	2.9 mm x 7 m 36.6 Kg
76.1 mm x	3.5 mm x 7 m 45.6 Kg
	4.0 mm x 7 m 49.8 Kg
	3.6 mm x 7 m 49.0 Kg
82.5 mm x	4.0 mm x 7 m 54.2 Kg
	3.6 mm x 7 m 61.0 Kg
101.6 mm x	4.5 mm x 7 m 75.4 Kg
	4.0 mm x 7 m 76.0 Kg
114.3 mm x	4.5 mm x 7 m 85.3 Kg



PT. SAPTA SUMBER LANCAR
STEEL STOCKIST, SUPPLIER AND SERVICES
Office : Ngagel Jaya Utara no. 56, Surabaya - 60284

P : +62 31 9944 3555, +62 31 9944 3777
F : +62 31 9944 5000
E : sales@sapta.co